

LANARTEX srl

Via I Maggio, 27 59013 Oste - Montemurlo (PO)

Tel.: 0574-071701 Fax: 0574-899903

e-mail: labo@lanartex.it Internet: www.lanartex.it





LAB N° 0572

MESSRS: ABITEX SRL VIA E. FERMI, 9/11 35010 CADONEGHE (PD) ITALIA REPORT NR.
REPORT DATE
ACCEPTANCE DATE
START TEST DATE
END TEST DATE
SAMPLING BY CUSTOMER

1902202-001 06/06/201903/06/2019
03/06/2019
06/06/2019

TEST REPORT

SAMPLE DESCRIPTION

FABRIC ART. ITALIAN BANG

THE REPORT IS MADE BY THE FOLLOWING TESTS:

TEST METHOD ACCREDIA

6012001 Assessment of the ignitability of upholstery fabric - Cigarette BS 5852-1:1979 6012002 Assessment of the ignitability of upholstery fabric - Match BS 5852-1:1979

Technical Manager

Dott.ssa Valentina Guidotti

Managing Director

Patrizia Rosati

(*) = Test marked with asterisk are not accredited ACCREDIA.

Limits of use for ACCREDIA brand: LANARTEX is a lab accredited by ACCREDIA and therefore it complying with its obbligations under the grant agreement signed with it. ACCREDIA brand can't be used on test materials, it can't also be used to imply the products certification.

The results contained in this report relates only to the sample tested and not to the lot / batch they want to represent. This test report can't be reproduced in part without written permission of LANARTEX.

MD 026/15 - 28/07/2016 Pagina 1\3



LANARTEX srl

Via I Maggio, 27 59013 Oste - Montemurlo (PO)

Tel.: 0574-071701 Fax: 0574-899903

e-mail: labo@lanartex.it Internet: www.lanartex.it





LAB N° 0572

TEST REPORT

MESSRS: ABITEX SRL VIA E. FERMI, 9/11 35010 CADONEGHE (PD) ITALIA

 REPORT NR.
 1902202-001

 REPORT DATE
 06/06/2019

 ACCEPTANCE DATE
 03/06/2019

 START TEST DATE
 03/06/2019

 END TEST DATE
 06/06/2019

 SAMPLING BY CUSTOMER

NOTES ANALYTICAL TESTS

 6012001 Assessment of the ignitability of upholstery fabric -Cigarette

BS 5852-1:1979

The above test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a means of assessing the full potential fire hazard of the materials in use; The test is been executed according with Furnishings (Fire) (Safety) Regulations 1988 n°1324, amd in 1989, 1993 and 2010, Schedule 4 - Part 1 (i.s. 0);

All outer covers that have been chemically treated to reduce their ignitability shall be subjected to the water soaking and drying procedure prior to being conditioned. This requirement applies to all methods of treatment, including back coating, which are applied to material covers that are finished in all other respects. It does not apply when the cover material is manufactured from materials that are formulated to be, or are inherently, flame retardant. Where it is not known whether the material has been so treated or not, the water soaking and drying procedure shall be carried out.

Acclimatization: At least 16 hours at 20 ± 5 °C e 50 % ± 20 % RH; Ignition source (i.s.): Ignition source 0 - Smouldering cigarette.

Filling material: PU non-FR (20-22 Kg/m3) SS20 supplied by the laboratory.

Off ignition source.

6012002 Assessment of the ignitability of upholstery fabric - Match BS 5852-1:1979

The following test results regard exclusively the characteristics of flammability of upholstery fabrics in the particular conditions used during the test, they can be used as evaluation of potential fire risk, of materials or products, in their final end use; The test is been executed according with Furnishings (Fire) (Safety) Regulations 1988 n°1324, amd in 1989, 1993 and 2010, Schedule 5 - Part 1 (i.s. 1);

All outer covers that have been chemically treated to reduce their ignitability shall be subjected to the water soaking and drying procedure prior to being conditioned. This requirement applies to all methods of treatment, including back coating, which are applied to material covers that are finished in all other respects. It does not apply when the cover material is manufactured from materials that are formulated to be, or are inherently, flame retardant. Where it is not known whether the material has been so treated or not, the water soaking and drying procedure shall be carried out.

Acclimatization: At least 16 hours at 20 ± 5 °C e 50 % ± 20 % RH; Ignition source (i.s.): Ignition source 1 - Match equivalent

Filling material: PU non-FR (20-22 Kg/m3) SS20 supplied by the laboratory.

GENERAL NOTES

(*) = Test marked with asterisk are not accredited ACCREDIA.

Limits of use for ACCREDIA brand: LANARTEX is a lab accredited by ACCREDIA and therefore it complying with its obbligations under the grant agreement signed with it. ACCREDIA brand can't be used on test materials, it can't also be used to imply the products certification.

The results contained in this report relates only to the sample tested and not to the lot / batch they want to represent. This test report can't be reproduced in part without written permission of LANARTEX.

LANARTEX srl ; Via I Maggio,27 – 59013 Oste - Montemurlo (PO)
Tel +39 0574 071701 Fax +39 0574 899903 e mail : labo@lanartex.it - web : www.lanartex.it

MD 026/15 - 28/07/2016 Pagina 2\3



LANARTEX srl

Via I Maggio, 27

59013 Oste - Montemurlo (PO)

Tel.: 0574-071701 Fax: 0574-899903

e-mail: labo@lanartex.it Internet: www.lanartex.it





LAB N° 0572

TEST REPORT

MESSRS: ABITEX SRL VIA E. FERMI, 9/11 35010 CADONEGHE (PD) ITALIA

 REPORT NR.
 1902202-001

 REPORT DATE
 06/06/2019

 ACCEPTANCE DATE
 03/06/2019

 START TEST DATE
 03/06/2019

 END TEST DATE
 06/06/2019

SAMPLING BY CUSTOMER

Tests	M.U.	Results	Method
6012001 Assessment of the ignitability of up fabric - Cigarette	pholstery		BS 5852-1:1979
Data declared by the customer	Sample chemically treated to reduce the ignitability		
Pretreatment	Water soak 40 °C - 30 min		
Kind of sample		Cover fabric	
Test 1 - Combustion with flame	Yes/No	NO	
Test 1 - Progressive smouldering	Yes/No	NO	
Test 1 - Result		PASS	
Test 2 - Combustion with flame	Yes/No	NO	
Test 2 - Progressive smouldering	Yes/No	NO	
Test 2 - Result		PASS	
6012002 Assessment of the ignitability of upholstery			BS 5852-1:1979
fabric - Match			
Data declared by the customer	Sample chemically treated to reduce the ignitability		
Pretreatment	Water soak 40 °C - 30 min		
Kind of sample		Cover fabric	
Test 1 - Combustion with flame	S	1	
Test 1 - Progressive smouldering	s	15	
Test 1 - Result		PASS	
Test 2 - Combustion with flame	S	2	
Test 2 - Progressive smouldering	S	16	
Test 2 - Result		PASS	

END OF REPORT

Limits of use for ACCREDIA brand: LANARTEX is a lab accredited by ACCREDIA and therefore it complying with its obbligations under the grant agreement signed with it. ACCREDIA brand can't be used on test materials, it can't also be used to imply the products certification.

The results contained in this report relates only to the sample tested and not to the lot / batch they want to represent. This test report can't be reproduced in part without written permission of LANARTEX.

MD 026/15 - 28/07/2016 Pagina 3\3

^{(*) =} Test marked with asterisk are not accredited ACCREDIA.