

**MESSRS.:**  
**ABITEX SRL**  
**VIA CASALI 48**  
**33048 SAN GIOVANNI AL**  
**NATISONE (33)**  
**ITALIA**

**REPORT NR.** 1403113-001  
**REPORT DATE** 29/09/2014  
ACCEPTANCE DATE 24/09/2014  
START TEST DATE 24/09/2014  
END TEST DATE 29/09/2014  
SAMPLING BY CUSTOMER

## TEST REPORT

SAMPLE DESCRIPTION: MOKA YEMEN

TEST	M.U	RESULTS	EXPANDED UNCERTAINTY <sup>1</sup>
<b>6012021 Assessment of the ignitability of upholstery fabric - Cigarette</b>			
<b>Method:</b>	EN 1021-1:2006 - Assessment of the ignitability of upholstery fabric - Cigarette		
Test 1 - Combustion with flame	sec	0	
Test 1 - Progressive smouldering	sec	0	
Test 1 - Result		N.I.	
Test 2 - Combustion with flame	sec	0	
Test 2 - Progressive smouldering	sec	0	
Test 2 - Result		N.I.	

Filling material: PU HR30S (30-33 Kg/m<sup>3</sup>) supplied by the laboratory.  
Pretreatment: None

The following test results regard exclusively the characteristics of flammability of upholstery fabrics in the particular conditions used during the test, they can be used as evaluation of potential fire risk, of materials or products, in their final end use;  
Acclimatization: At least 16 hours at 20 ± 5 °C e 50 % ± 20 % RH; Ignition source (i.s.): Ignition source 0 - Smouldering cigarette.

**(\*) = the tests marked with asterisk are not accredited by Accredia.**

<sup>1</sup> U: the reported uncertainty is the extended uncertainty calculated using a coverage factor of 2 which gives a level of confidence approximatively of 95%.

		<b>REPORT NR.</b>	<b>1403113-001</b>
		<b>REPORT DATE</b>	<b>29/09/2014</b>
<b>TEST</b>	<b>M.U.</b>	<b>RESULTS</b>	<b>EXPANDED UNCERTAINTY<sup>1</sup></b>

**6012031 Assessment of the ignitability of upholstery fabric - Match**

**Method:** EN 1021-2:2006 - Assessment of the ignitability of upholstery fabric - Match

Test 1 - Combustion with flame	sec	0
Test 1 - Progressive smouldering	sec	10
Test 1 - Result		N.I.
Test 2 - Combustion with flame	sec	0
Test 2 - Progressive smouldering	sec	10
Test 2 - Result		N.I.

Filling material: PU HR30S (30-33 Kg/m<sup>3</sup>) supplied by the laboratory.  
Pretreatment: None

The following test results regard exclusively the characteristics of flammability of upholstery fabrics in the particular conditions used during the test, they can be used as evaluation of potential fire risk, of materials or products, in their final end use; The test is been executed according with Furnishings (Fire) (Safety) Regulations 1988 n°1324, amd in 1989, 1993 and 2010, Schedule 5 - Part 1 (i.s. 1); Acclimatization: At least 16 hours at 20 ± 5 °C e 50 % ± 20 % RH; Ignition source (i.s.): Ignition source 1 - Match equivalent flame.

The sample name and, when relevant, its description, are given by the orderer, and LANARTEX does not assume responsibility on this matter. This test report relates to the sample submitted for the test and no others. Additions, deletions or alterations are not permitted. This test report must always be reproduced in its entirety. Unless otherwise stated, sampling has been carried out by the orderer. The use of ILAC-ACCREDIA brands is limited by the terms of the agreement ACCREDIA-LANARTEX.

-----  
**END OF REPORT**  
-----

**Managing Director**

Patrizia Rosati  
-----

**(\*) = the tests marked with asterisk are not accredited by Accredia.**

<sup>1</sup> U: the reported uncertainty is the extended uncertainty calculated using a coverage factor of 2 which gives a level of confidence approximatively of 95%.