

**MESSRS.:**  
**ABITEX SRL**  
**VIA CASALI 48**  
**33048 SAN GIOVANNI AL**  
**NATISONE (UD)**  
**ITALIA**

**REPORT NR.** 1601841-004  
**REPORT DATE** 12/05/2016  
ACCEPTANCE DATE 09/05/2016  
START TEST DATE 09/05/2016  
END TEST DATE 12/05/2016  
SAMPLING BY CUSTOMER

## TEST REPORT

SAMPLE DESCRIPTION: 08164 001 140 900 ODINO VINACCIA P.TA 27694 0164041

TEST	M.U	RESULTS	EXPANDED UNCERTAINTY <sup>1</sup>
<b>6011002 Assessment of the ignitability of upholstery fabric - California test</b>			
<b>Method:</b> TB 117:2013 - Assessment of the ignitability of upholstery fabric - California test			
Initial - Specimen 1 - Char length	inch	0,3	
Initial - Specimen 2 - Char length	inch	0,2	
Initial - Specimen 3 - Char length	inch	0,3	
Initial - Specimen 1 - SE	Yes/No	NO	
Initial - Specimen 2 - SE	Yes/No	NO	
Initial - Specimen 3 - SE	Yes/No	NO	
Initial - Specimen 1 - SB45	Yes/No	NO	
Initial - Specimen 2 - SB45	Yes/No	NO	
Initial - Specimen 3 - SB45	Yes/No	NO	
Initial - Specimen 1 - TOF	Yes/No	NO	
Initial - Specimen 2 - TOF	Yes/No	NO	
Initial - Specimen 3 - TOF	Yes/No	NO	
Final class		PASS	

*Codes used:*

*SE: Self-extinguished;*

*SB45: Smolder beyond 45 min;*

*TOF: Transitions to open flaming;*

*MNR: Measurement not recorded as smoldering exceeded 45 min or specimen transitioned to open flames. The data are referred to TB*

**(\*) = the tests marked with asterisk are not accredited by Accredia.**

<sup>1</sup> U: the reported uncertainty is the extended uncertainty calculated using a coverage factor of 2 which gives a level of confidence approximatively of 95%.



# LABORATORIO PROVE, ANALISI RICERCHE TESSILI

LANARTEX di Rosati Patrizia & C. Sas  
Via I° Maggio, 27  
59013 Montemurlo (PO)  
Tel. 0574-071701 Fax: 0574-899903  
e-mail: labo@lanartex.it  
Partita IVA: 02055730978



LAB n° 0572

		<b>REPORT NR.</b>	<b>1601841-004</b>
		<b>REPORT DATE</b>	<b>12/05/2016</b>
<b>TEST</b>	<b>M.U.</b>	<b>RESULTS</b>	<b>EXPANDED UNCERTAINTY <sup>1</sup></b>

117:2013 - Section NR.1

*Unrepeatable tests to exhaustion test material.*

The sample name and, when relevant, its description, are given by the orderer, and LANARTEX does not assume responsibility on this matter. This test report relates to the sample submitted for the test and no others. Additions, deletions or alterations are not permitted. This test report must always be reproduced in its entirety. Unless otherwise stated, sampling has been carried out by the orderer. The use of ILAC-ACCREDIA brands is limited by the terms of the agreement ACCREDIA-LANARTEX.

-----  
**END OF REPORT**  
-----

**Managing Director**

Patrizia Rosati



**(\*) = the tests marked with asterisk are not accredited by Accredia.**

<sup>1</sup> U: the reported uncertainty is the extended uncertainty calculated using a coverage factor of 2 which gives a level of confidence approximatively of 95%.

LANARTEX di Rosati Patrizia C. Sas ; Via I° Maggio,27 – 59013 Oste - Montemurlo (PO)  
Tel +39 0574 071701 Fax +39 0574 899903 e mail : labo@lanartex.it - web : www.lanartex.it