

MESSRS.:
ABITEX SRL
VIA CASALI, 48
33048 SAN GIOVANNI AL
NATISONE (UD)
ITALIA

REPORT NR. 1503786-003
REPORT DATE 11/12/2015
ACCEPTANCE DATE 09/12/2015
START TEST DATE 09/12/2015
END TEST DATE 11/12/2015
SAMPLING BY CUSTOMER

TEST REPORT

SAMPLE DESCRIPTION: 02353 001 140 101 GANESHA BIANCO P.TA CF40234/28 3 100380

TEST	M.U	RESULTS	EXPANDED UNCERTAINTY ¹
6011002 Assessment of the ignitability of upholstery fabric - California test			
Method: TB 117:2013 - Assessment of the ignitability of upholstery fabric - California test			
Initial - Specimen 1 - Char length	inch	0,3	
Initial - Specimen 2 - Char length	inch	0,4	
Initial - Specimen 3 - Char length	inch	0,6	
Initial - Specimen 1 - SE	Yes/No	NO	
Initial - Specimen 2 - SE	Yes/No	NO	
Initial - Specimen 3 - SE	Yes/No	NO	
Initial - Specimen 1 - SB45	Yes/No	NO	
Initial - Specimen 2 - SB45	Yes/No	NO	
Initial - Specimen 3 - SB45	Yes/No	NO	
Initial - Specimen 1 - TOF	Yes/No	NO	
Initial - Specimen 2 - TOF	Yes/No	NO	
Initial - Specimen 3 - TOF	Yes/No	NO	
Final class		PASS	

Codes used:

SE: Self-extinguished;

SB45: Smolder beyond 45 min;

TOF: Transitions to open flaming;

MNR: Measurement not recorded as smoldering exceeded 45 min or specimen transitioned to open flames. The data are referred to TB 117:2013 - Section NR.1

(*) = the tests marked with asterisk are not accredited by Accredia.

¹ U: the reported uncertainty is the extended uncertainty calculated using a coverage factor of 2 which gives a level of confidence approximatively of 95%.

		REPORT NR.	1503786-003
		REPORT DATE	11/12/2015
TEST	M.U.	RESULTS	EXPANDED UNCERTAINTY ¹

Unrepeatable tests to exhaustion test material.

The sample name and, when relevant, its description, are given by the orderer, and LANARTEX does not assume responsibility on this matter. This test report relates to the sample submitted for the test and no others. Additions, deletions or alterations are not permitted. This test report must always be reproduced in its entirety. Unless otherwise stated, sampling has been carried out by the orderer. The use of ILAC-ACCREDIA brands is limited by the terms of the agreement ACCREDIA-LANARTEX.

END OF REPORT

Managing Director

Patrizia Rosati



(*) = the tests marked with asterisk are not accredited by Accredia.

¹ U: the reported uncertainty is the extended uncertainty calculated using a coverage factor of 2 which gives a level of confidence approximatively of 95%.