



**Centro Tessile Serico Sostenibile Srl**  
via Castelnuovo, 3 - 22100 Como Italia  
Pho +39 031 3312111/120 Fax: +39 0313312149  
Amministrazione/Contabilità +39 031 3312102-154  
P. IVA - C.F. 003900470133  
Capitale sociale euro 600000,00 iv  
mailbox@textilecomo.com  
www.textilecomo.com



LAB N° 0045 L

Test Report No.:	<b>2406227-002</b>	Customer Code 07664
Date Test Report	<b>04-nov-24</b>	Dear:
Acceptance:	<b>2406227</b>	<b>ABITEX SRL</b>
Arrival date sample	<b>28-ott-24</b>	via del Cristo 84
Start date test	<b>28-ott-24</b>	33044 MANZANO (UD) Italia
End date test	<b>04-nov-24</b>	C.a. sig. Matteo Bortolossi
References:	DDT. 12907 dated 23-oct-2024	Phone: +39 0432 746060
Sampling Mode:	Sampling by Customer *	

[C] Item:	<b>B-GREEN GRS GROVGLIO (04434)</b>
[C] Declared Composition:	<b>52% recycled PL - 48% PL</b>
[C] End use:	<b>furnishing</b>
[C] Typology:	<b>fabric</b>
[C] Note:	<b>batch n. 06271</b>
Return:	<b>no requested</b>

## Test Results

Test	Method	U.M.	Result
* <b>90081 RISTAMPA RAPPORTI DI PROVA</b>			.
<b>15066 UPHOLSTERY FURNITURE</b>	<b>NFPA 260:2024 (except Par. 4.2 and 6.6)</b>		.
<b>COMPONENTS: ASSESSMENT OF THE IGNITABILITY BY SMOULDERING CIGARETTE</b>			
Start date test	31/10/2024		
End date test	04/11/2024		
Instrument:	Mini Mock Up Tester		
Test carried out on			COVER FABRIC
Pretreatment carried out			none
Conditioning of sample			24 h at 21 ± 3 °C, <65% r.h.
Testing temperature and r.h.			17°C, 65% r.h.
Ignition source			NON filtered standard cigarette SRM 1196
TEST RESULT			CLASS 1
Deviations from the method			none
Annex n.			1F
Details of the test results related to each specimen can be seen in the annex of this test report.			

(\*) = The tests marked in this way are not accredited by Accredia

The Results contained in this Report refer only to the sample as received and to the objects tested and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.

This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.

[C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.



**Centro Tessile Serico Sostenibile Srl**  
via Castelnuovo, 3 - 22100 Como Italia  
Pho +39 031 3312111/120 Fax: +39 0313312149  
Amministrazione/Contabilità +39 031 3312102-154  
P. IVA - C.F. 003900470133  
Capitale sociale euro 600000,00 iv  
mailbox@textilecomo.com



LAB N° 0045 L

Test Report No.: **2406227-002**

Test	Method	U.M.	Result
------	--------	------	--------

**The Laboratory Manager**

Fausto Albonico

-----  
**END OF REPORT**  
-----

(\*) = The tests marked in this way are not accredited by Accredia

The Results contained in this Report refer only to the sample as received and to the objects tested and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.

This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.

[C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.



**Centro Tessile Serico Sostenibile Srl**  
Via Castelnuovo, 3 – 22100 Como Italia  
Tel. +39 031331211 Fax +39 0313312149  
Amministrazione/Contabilità +39 0313312102-154  
P.IVA – C.F. 03900470133  
Capitale sociale euro 600.000,00 iv  
[mailbox@textilecomo.com](mailto:mailbox@textilecomo.com)  
[www.textilecomo.com](http://www.textilecomo.com)



LAB N° 0045 L

Allegato n. 1F al rapporto di prova n. / Annex n. 1F to test report n. 2406227-002

**DETTAGLIO DEI RISULTATI DI PROVA**  
**DETAILS OF TEST RESULTS**

Prova eseguita in conformità a NPFA 260:2024

Metodo di prova e sistema di classificazione per la valutazione dell'infiammabilità di componenti di mobili imbottiti

Test carried out according to NPFA 260:2024

Standard Methods of Tests and Classification System for Cigarette Ignition Resistance of Components of Upholstered Furniture

Materiali dell'assemblaggio / Materials of test assembly:	
Imbottitura prevista dal metodo NFPA 260 <i>Upholstery filling specification according to NFPA 260</i>	Schiuma poliuretana NON IGNIFUGA con densità di 28-29,6 kg/m <sup>3</sup> <i>Non fire-retardant polyurethane foam with a density of 28-29,6 kg/m<sup>3</sup></i>
Rivestimento esterno / Outer cover	vedasi descrizione articolo / see article description
Pretrattamento del campione / Sample pretreatment:	Pretrattamento non previsto dal metodo / Pretreatment not required by method
Sorgente prevista dal metodo NFPA260 <i>Source according to NFPA 260</i>	Sigaretta standard senza filtro SRM 1196 <i>NON filtered cigarette SRM 1196</i>

**Par. 6.2 COVER FABRIC TEST**

Provetta n. / Specimen nr.	1	2	3	Requisiti Requirements	
Totale combustione della sigaretta (SI/NO) <i>Total combustion of the cigarette (YES / NO)</i>	SI/YES	SI/YES	SI/YES	-	-
Durata di combustione senza fiamma dall'applicazione della sorgente (min) <i>Time of progressive smouldering from placement of the source (min)</i>	27	28	28	<45 min	>45 min
Dimensione del danneggiamento verticale (mm) / Size of vertical char (mm)	20	22	22	<45 mm	>45 mm
Combustione progressiva continuata (SI/NO) <i>Progressive smouldering observed (YES / NO)</i>	NO	NO	NO	NO	YES
Transizione a combustione CON fiamma (SI/NO) <i>Mock-up test specimen transitions to open flaming (YES / NO)</i>	NO	NO	NO	NO	YES
<b>Risultato / Result</b>	<b>Class 1</b>	<b>Class 1</b>	<b>Class 1</b>	<b>Class 1</b>	<b>Class 2</b>

**IL CAMPIONE TESTATO SODDISFA I REQUISITI DELLA CLASSE 1**


I risultati di prova di cui sopra riguardano esclusivamente l'accendibilità della combinazione di materiali nelle particolari condizioni di prova. Essi non sono destinati a essere utilizzati come mezzo di valutazione della pericolosità d'incendio potenziale globale dei materiali nella destinazione d'uso.

La probabilità che la conformità attribuita corrisponda al vero è pari al 95%.

*The following test result relate only to the ignitability of the combination of materials under the particular conditions of test.*

*They are not intended as a means of assessing the full potential fire hazard of the material in use.*

*The probability that the criteria represent the truth observation is equal to 95%.*

  
Il Responsabile Laboratorio  
The Laboratory Manager  
Fausto Albonico

I Risultati contenuti nel presente Allegato si riferiscono esclusivamente al campione così come ricevuto e agli oggetti provati e non implicano una approvazione del prodotto testato da parte del Laboratorio del Centro Tessile Serico Sostenibile Srl. Il presente Rapporto non può essere riprodotto parzialmente, salvo preventiva autorizzazione scritta del Laboratorio Centro Tessile Serico Sostenibile Srl / The Results contained in this Annex refer only to the sample as received and to the objects tested and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory