

MESSRS.:
ABITEX SRL
VIA CASALI 48
33048 SAN GIOVANNI AL
NATISONE (UD)
ITALIA

REPORT NR. 1600028-003
REPORT DATE 14/01/2016
ACCEPTANCE DATE 11/01/2016
START TEST DATE 11/01/2016
END TEST DATE 14/01/2016
SAMPLING BY CUSTOMER

TEST REPORT

SAMPLE DESCRIPTION: 02059 001 140 200 SOLARIS CONTOUR BLACK P.TA EF3500521

TEST	M.U	RESULTS	EXPANDED UNCERTAINTY ¹
6012001 Assessment of the ignitability of upholstery fabric - Cigarette			
Method: BS 5852-1:1979 - Assessment of the ignitability of upholstery fabric - Cigarette			
Kind of sample		COVER FABRIC	
Test 1 - Combustion with flame	sec	0"	
Test 1 - Progressive smouldering	sec	0"	
Test 1 - Result		PASS	
Test 2 - Combustion with flame	sec	0"	
Test 2 - Progressive smouldering	sec	0"	
Test 2 - Result		PASS	

Method: BS 5852-1:1979 - Assessment of the ignitability of upholstery fabric - Cigarette

Kind of sample		COVER FABRIC	
Test 1 - Combustion with flame	sec	0"	
Test 1 - Progressive smouldering	sec	0"	
Test 1 - Result		PASS	
Test 2 - Combustion with flame	sec	0"	
Test 2 - Progressive smouldering	sec	0"	
Test 2 - Result		PASS	

Filling material: PU non-FR (20-22 Kg/m3) SS20 supplied by the laboratory.
Pretreatment: None

The following test results regard exclusively the characteristics of flammability of upholstery fabrics in the particular conditions used during the test, they can be used as evaluation of potential fire risk, of materials or products, in their final end use; The test is been executed according with Furnishings (Fire) (Safety) Regulations 1988 n°1324, amd in 1989 , 1993 and 2010, Schedule 4 - Part 1 (i.s. 0); Acclimatization: At least 16 hours at 20 ± 5 °C e 50 % ± 20 % RH; Ignition source (i.s.): Ignition source 0 - Smouldering cigarette.

(*) = the tests marked with asterisk are not accredited by Accredia.

¹ U: the reported uncertainty is the extended uncertainty calculated using a coverage factor of 2 which gives a level of confidence approximatively of 95%.

TEST	M.U.	RESULTS	EXPANDED UNCERTAINTY ¹
------	------	---------	-----------------------------------

REPORT NR. 160028-003
REPORT DATE 14/01/2016

6012002 Assessment of the ignitability of upholstery fabric - Match

Method: BS 5852-1:1979 - Assessment of the ignitability of upholstery fabric - Match

Kind of sample		COVER FABRIC
Test 1 - Combustion with flame	sec	0"
Test 1 - Progressive smouldering	sec	6"
Test 1 - Result		PASS
Test 2 - Combustion with flame	sec	0"
Test 2 - Progressive smouldering	sec	9"
Test 2 - Result		PASS

*Filling material: PU non-FR (20-22 Kg/m3) SS20 supplied by the laboratory.
Pretreatment: None*

The following test results regard exclusively the characteristics of flammability of upholstery fabrics in the particular conditions used during the test, they can be used as evaluation of potential fire risk, of materials or products, in their final end use; The test is been executed according with Furnishings (Fire) (Safety) Regulations 1988 n°1324, amd in 1989 , 1993 and 2010, Schedule 5 - Part 1 (i.s. 1); Acclimatization: At least 16 hours at 20 ± 5 °C e 50 % ± 20 % RH; Ignition source (i.s.): Ignition source 1 - Match equivalent flame.

The sample name and, when relevant, its description, are given by the orderer, and LANARTEX does not assume responsibility on this matter. This test report relates to the sample submitted for the test and no others. Additions, deletions or alterations are not permitted. This test report must always be reproduced in its entirety. Unless otherwise stated, sampling has been carried out by the orderer. The use of ILAC-ACCREDIA brands is limited by the terms of the agreement ACCREDIA-LANARTEX.

END OF REPORT

Managing Director

Patrizia Rosati



(*) = the tests marked with asterisk are not accredited by Accredia.

¹ U: the reported uncertainty is the extended uncertainty calculated using a coverage factor of 2 which gives a level of confidence approximatively of 95%.