

**MESSRS.:
ABITEX SRL
VIA CASALI 48
33048 SAN GIOVANNI AL
NATISONE (UD)
ITALIA**

REPORT NR. 1600028-004
REPORT DATE 14/01/2016
ACCEPTANCE DATE 11/01/2016
START TEST DATE 11/01/2016
END TEST DATE 14/01/2016
SAMPLING BY CUSTOMER

TEST REPORT

SAMPLE DESCRIPTION: 02059 001 140 200 SOLARIS CONTOUR BLACK P.TA EF3500521

TEST	M.U	RESULTS	EXPANDED UNCERTAINTY ¹
------	-----	---------	-----------------------------------

6011002 Assessment of the ignitability of upholstery fabric - California test

Method: TB 117:2013 - Assessment of the ignitability of upholstery fabric - California test

Initial - Specimen 1 - Char length	inch	0,8	
Initial - Specimen 2 - Char length	inch	0,8	
Initial - Specimen 3 - Char length	inch	0,6	
Initial - Specimen 1 - SE	Yes/No	NO	
Initial - Specimen 2 - SE	Yes/No	NO	
Initial - Specimen 3 - SE	Yes/No	NO	
Initial - Specimen 1 - SB45	Yes/No	NO	
Initial - Specimen 2 - SB45	Yes/No	NO	
Initial - Specimen 3 - SB45	Yes/No	NO	
Initial - Specimen 1 - TOF	Yes/No	NO	
Initial - Specimen 2 - TOF	Yes/No	NO	
Initial - Specimen 3 - TOF	Yes/No	NO	
Final class		PASS	

Codes used:

SE: Self-extinguished;

SB45: Smolder beyond 45 min;

TOF: Transitions to open flaming;

MNR: Measurement not recorded as smoldering exceeded 45 min or specimen transitioned to open flames. The data are referred to TB

(*) = the tests marked with asterisk are not accredited by Accredia.

¹ U: the reported uncertainty is the extended uncertainty calculated using a coverage factor of 2 which gives a level of confidence approximatively of 95%.

LANARTEX di Rosati Patrizia C. Sas ; Via I° Maggio,27 – 59013 Oste - Montemurlo (PO)
Tel +39 0574 071701 Fax +39 0574 899903 e mail : labo@lanartex.it - web : www.lanartex.it

		REPORT NR.	1600028-004
		REPORT DATE	14/01/2016
TEST	M.U.	RESULTS	EXPANDED UNCERTAINTY ¹

117:2013 - Section NR.1

The sample name and, when relevant, its description, are given by the orderer, and LANARTEX does not assume responsibility on this matter. This test report relates to the sample submitted for the test and no others. Additions, deletions or alterations are not permitted. This test report must always be reproduced in its entirety. Unless otherwise stated, sampling has been carried out by the orderer. The use of ILAC-ACCREDIA brands is limited by the terms of the agreement ACCREDIA-LANARTEX.

END OF REPORT

Managing Director

Patrizia Rosati



(*) = the tests marked with asterisk are not accredited by Accredia.

¹ U: the reported uncertainty is the extended uncertainty calculated using a coverage factor of 2 which gives a level of confidence approximatively of 95%.

LANARTEX di Rosati Patrizia C. Sas ; Via I° Maggio,27 – 59013 Oste - Montemurlo (PO)
Tel +39 0574 071701 Fax +39 0574 899903 e mail : labo@lanartex.it - web : www.lanartex.it