



19.28838R1

**I I S G**



# TEST REPORT

**ABITEX SRL**

**LAB NO:** (IT) 19.28838R1


**VIA DEL CRISTO 84  
33044 MANZANO**

**DATE IN:** 18/6/2019  
**DATE OUT:** 5/7/2019

**PAGE:** 1 OF 4

**ATTN:** Sig. Matteo Bortolossi

<b>Sample Description:</b>	ART. TERASKIN		
<b>Color:</b>	105	<b>Item:</b>	ARTIFICIAL LEATHER
<b>Labeled Fiber Content:</b>	55% SILICONE 45% POLYESTER		





19.28838R1

I I S G



<b>Requested Test:</b>	<b>LEATHER-PHYSICAL AND MECHANICAL TESTS-DETERMINATION OF COLD CRACK TEMPERATURE OF SURFACE COATINGS - ISO 17233:2017</b> ◇
	<b>LEATHER: PHYSICAL AND MECHANICAL TESTS – DETERMINATION OF THICKNESS - ISO 2589:2016</b>

◇ Test assigned to external laboratory

**NOTE ON REVISION: We have revised the report in order to add a second analysis EN ISO 17233:2017 performed at the temperature of -40°C and to correct the temperature from 10°C to – 10°C of the first analysis (typo mistake).**

Laboratory Supervisor  
Giovanni Moro

**REMARKS**

1. This report is intended for your exclusive use. Any copying or replication of this report to or for any other person or entity, or use of our name or trademark, is permitted only with our written permission.
2. Our report is limited to the test samples identified herein. The results set forth in this report are not necessarily indicative or representative of the statistical quality or characteristics of the lot from which a test sample was taken or any similar or identical product unless specifically and expressly noted.
3. Our report includes all the tests requested by you and the results thereof. You shall have thirty days from receipt of this report to request additional testing of the samples or to notify us of any errors or omissions relating to our report; provided, however, such notice shall be in writing and shall specifically address the issue you wish to raise. A failure to raise such issue within the prescribed time shall constitute your unqualified acceptance of the completeness of this report, the tests conducted and the correctness of the report contents.
4. Information contained in this report will be sent to the final client according to the procedure established in his manual or for Lab Procedure.
5. The client is responsible for the sampling, the shipment and the delivery of the sample.



19.28838R1

**I I S G**



Testing date:

From: 18/6/2019

To: 5/7/2019

<b>TEST</b>	<b>LEATHER-PHYSICAL AND MECHANICAL TESTS-DETERMINATION OF COLD CRACK TEMPERATURE OF SURFACE COATINGS</b>
<b>METHOD</b>	<b>ISO 17233:2017</b> ◊
Temperature of test: - 10° C	
<b>RESULTS: no breakage</b>	
Note: //	

<b>TEST</b>	<b>LEATHER-PHYSICAL AND MECHANICAL TESTS-DETERMINATION OF COLD CRACK TEMPERATURE OF SURFACE COATINGS</b>
<b>METHOD</b>	<b>ISO 17233:2017</b> ◊
Temperature of test: - 40°C	
<b>RESULTS: no breakage</b>	
Note: //	



19.28838R1

**I I S G**



<b>TEST</b>	<b>LEATHER: PHYSICAL AND MECHANICAL TESTS – DETERMINATION OF THICKNESS</b>	
<b>METHOD</b>	<b>ISO 2589:2016</b>	
Conditioning at 20° C and 65 % R.H.		
Measurement n° 1	0.84	mm
Measurement n° 2	0.85	mm
Measurement n° 3	0.84	mm
Measurement n° 4	0.86	mm
Measurement n° 5	0.85	mm
Note: //		

**\*\*\*END OF REPORT\*\*\***